

# DOL 1470 Max Satin

## Satin Clear Cast Overlamine

Revision 0

### Introduction

Avery Dennison® DOL 1470 Max Satin is a conformable premium quality UV stable satin cast overlamine designed for use as a protective overlaminating film for digitally printed images and is suitable for durable outdoor images on irregular surfaces, such as vehicles, where satin finish and the excellent conformability is necessary.

### Common Applications


- Cars & vans
- Corrugated trucks
- Flat sided trucks
- Exterior signage
- Window graphics
- Internally illuminated signage
- Marine vessels\*



**Face Film**  
32 micron satin clear  
UV stable cast PVC



**Adhesive**  
Permanent acrylic



**Backing**  
50 micron one side coated  
transparent PET film



**Outdoor Life\*\***  
Up to 7 years

### Features

- Up to 1 year horizontal and 5 years vertical ICS Warranty in Zone 2
- Conformable film with excellent deep recess (channel) and compound curve performance in combination with our MPI 1105 series ultimate cast films
- Provides maximum UV and weathering protection with added abrasion and chemical resistance to printed graphics. Improves solvent, UV curable and latex inkjet outdoor image durability up to 5 years
- Brilliant transparency for bright, vivid images
- Dimensionally stable mottle reduction PET liner for easy converting
- Exceptional adhesion to solvent inkjet, UV curable inkjet, latex inkjet and screen printed graphics

### Conversion

- ☐ Flatbed cutters
- ☐ Friction fed cutters
- ☐ Die cutting
- ☐ Thermal transfer
- ☐ Screen printing
- ☐ Offset printing
- ☒ Cold overlaminating
- ☐ Electrostatic printing
- ☐ Eco solvent inkjet
- ☐ Solvent inkjet
- ☐ UV curable inkjet
- ☐ Latex inkjet

## Applications

- Refer to [Instructional Bulletin 4.06](#) for Processing Tips for Laminating Films (DOL)
- Refer to [Instructional Bulletin 1.16](#) for Conversion & Application of MPI 1105 EA RS for Vehicle Wrapping

## General

Roll width, length	1372mm, 1524mm	45.7m
Caliper, face film	ISO 534	32 micron
Caliper, face film & adhesive	ISO 534	57 micron
Gloss	@60°	30%
Elongation		Min 100%
Dimensional stability		0.4mm max
Adhesion, initial	ASTM 1000, Stainless steel	525 N/m
Adhesion, ultimate	ASTM 1000, Stainless steel	613 N/m
Shelf life	Stored at 22° C/50% RH	2 years
Flammability		Self extinguishing
Expected Durability**	Vertical exposure Horizontal Exposure	Up to 7 years Up to 1 year

## Thermal

Application temperature	Minimum: + 10°C
Temperature range	-40°C to +82°C

## Chemical

Humidity resistance	120 hours exposure	No effect
Corrosion resistance	120 hours exposure	No contribution to corrosion
Water resistance	48 hour immersion	No effect
Chemical resistance	Mild acids Mild alkalis	No effect No effect
Solvent resistance	Applied to aluminium	No effect exposed to: Oils, greases, aliphatic solvents, motor oils, heptanes, kerosene, JP-4 fuel

## Note

Materials have to be properly dried and cured before further processing, like laminating, varnishing, trimming, contour cutting or application. The residual solvents can otherwise change the products' specific features and properties.

### Important

Information on physical characteristics is based upon tests we believe to be reliable. The values listed herein are typical values and are not for use in specifications. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of any material for their specific use.

All technical data is subject to change without prior notice.

### \*\*Expected Durability

The expected durability of Avery Dennison films are defined as the expected performance life of the Avery Dennison graphic film(s) within Zone 1 of the Avery Dennison zone system, in outdoor vertical exposure conditions. The actual performance life will depend on a variety of factors, including selection and preparation of substrate, angle and direction of exposure, application methods, environmental conditions and cleaning/maintenance of the films. In case of films used in areas of high temperatures or humidity, high altitudes and industrially polluted areas the performance will be further reduced.

### Warranty

Avery Dennison® materials are manufactured under careful quality control and are warranted to be free from defect in material and workmanship. Any material shown to our satisfaction to be defective at the time of sale will be replaced without charge. Our aggregate liability to the purchaser shall in no circumstances exceed the cost of the defective materials supplied. No salesman, representative or agent is authorised to give guarantee, warranty, or make any representation contrary to the foregoing. All Avery Dennison® materials are sold subject to the above conditions, being part of our standard conditions of sale, a copy of which is available on request.

### ^^ Removability

Not removable when applied to nitrocellulose paints, fresh screen print inks, ABS, polystyrene & certain types of PVC.

### Expected Durability and Warranted Period Definitions

Expected durability is the expected period of time defined in the product data sheet, the product should, but is not warranted to, perform satisfactorily when applied in vertical exposure conditions as defined in [Instructional Bulletin 1.30](#). The warranted period as defined in the appropriate ICS Performance Guarantee Bulletin, is the maximum period of time Avery Dennison will warrant the finished products performance in accordance with ICS Performance Guarantee Terms and Conditions 1.0, provided that the film is properly stored, converted and installed in accordance with Avery Dennison guidelines.

## Testing Methods

### Dimensional stability:

Is measured on a 150 x 150 mm aluminium panel to which a specimen has been applied; 72 hours after application the panel is exposed for 48 hours to + 70°C, after which the shrinkage is measured.

### Adhesion:

(FTM-1, FINAT) is measured by peeling a specimen at a 180° angle from a stainless steel or float glass panel, 24 hours after the specimen has been applied under standardised conditions. Initial adhesion is measured 20 minutes after application of the specimen.

### Flammability:

A specimen applied to aluminium is subjected to the flame of a gas burner for 15 seconds. The film should stop burning within 15 seconds after removal from the flame.

### Temperature range:

A specimen applied to stainless steel is exposed at high and low temperatures and brought back to room temperature. 1 hour after exposure the specimen is examined for any deterioration. Note: Prolonged exposure to high and low temperatures in the presence of chemicals such as solvents, acids, dyes, etc. may eventually cause deterioration.

### Chemical Resistance:

All chemical tests are conducted with test panels to which a specimen has been applied. 72 hours after application the panels are immersed in the test fluid for the given test period. 1 hour after removing the panel from the fluid, the specimen is examined for any deterioration.

### Corrosion Resistance:

A specimen applied to aluminium is exposed to saline mist (5% salt) at 35°C. After exposure, the film is removed and the panel is examined for traces of corrosion.



Avery Dennison warrants that its Products meet its specifications. Avery Dennison gives no other express or implied guarantees or warranties with respect to the Products, including but not limited to, any implied warranties of merchantability, fitness for any particular use and/or non infringement. All Avery Dennison products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purposes. The period of warranty is one (1) year from the date of shipment unless expressly provided otherwise in the product data sheet. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <https://graphicsap.averydennison.com/terms>. Avery Dennison's aggregate liability to Purchaser, whether for negligence, breach of contract, misrepresentation or otherwise, shall in no circumstances exceed the price of the defective, non-conforming, damaged or undelivered Products which give rise to such liability as determined by net price invoices to Purchaser in respect of any occurrence or series of occurrences. In no circumstances shall Avery Dennison be liable to Purchaser for any indirect, incidental or consequential loss, damage or injury, including without limitation, loss of anticipated profits, goodwill, reputation, or losses or expenses resulting from third party claims. © 2024 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.